

Legeringsöversättning

EN AW Numerisk	Sverige SS (gammal beteckning)	USA AA	Tyskland	
			DIN	W-stoffnr.
1050A	4007	1050A	Al99,5	3.0255
1070A	4005	1070A	Al99,7	3.0275
1200	4010	1200	Al99	3.0205
1350	4008	1350	E-Al	3.0257
2007	4335	2007	AlCuMgPb	3.1645
2011	4355	2011	AlCuBiPb	3.1655
2014	4338	2014	AlCuSiMn	3.1255
2017A	-	2017A	AlCuMg1	3.1325
2024	-	2024	AlCuMg2	3.1355
2030	4335	2030	AlCuMgPb	-
3003	-	3003	AlMnCu	3.0517
3103	4054	3103	AlMn1	3.0515
5005	4106	5005	AlMg1	3.3315
5049	4115	5049	AlMg2Mn0,8	-
5052	4120	5052	AlMg2,5	3.3523
5083	4140	5083	AlMg4,5Mn	3.3547
5086	-	5086	AlMg4Mn	3.3545
5754	4125	5754	AlMg3	3.3535
6005	4107	6005	AlMgSi0,7	3.3210
6012	(4212-Pb)	6012	AlMgSiPb	-
6026	(4212-Pb)	6262	(AlMgSiPb)	-
6060	4103	6060	AlMgSi0,5	3.3206
6061	-	6061	AlMg1SiCu	3.3211
6063	4104	6063	AlMgSi1	3.2315
6082	4212	6082	AlMgSi1	3.2315
6101B	4102	6101B	E-AlMgSi0,5	3.3207
7020	4425	7020	AlZn4,5Mg1	3.4335
7022	-	7022	AlZnMgCu0,5	3.4345
7075	-	7075	AlZnMgCu1,5	3.4365



ALUTRADE

PROFILER MED ENGAGEMANG